









Ink Compatibility (all inks must be tested for compatibility)							
Solvent	Eco Solvent	UV	Screen Printing	Eradicable	Latex		
•	•	•			•		

Not eradicable. Decorative Methods: P.S. Vinyl, Silk Screen, Spray Paint, and Digitally Printable.

## Cooley/Commercial Graphics

WHERE SUSTAINABLE CHEMISTRY MAKES THE DIFFERENCE

#### cooleygroup.com

info@cooleygroup.com

### Global Headquarters and Manufacturing

50 Esten Avenue Pawtucket, RI 02860, USA +1 401.724.9000

Email: cginfo@cooleygroup.com

## R&D Innovation Center and Manufacturing

5 Slater Road Cranston, RI 02920, USA +1 401.724.9000

### Manufacturing

861 Quality Drive Lancaster, SC 29720, USA +1 803.289.1846

#### **European Headquarters**

In der Steinwiese 5 57074 Siegen Germany +49 (0) 271.770.1777





**Weathertyte**® *PLUS* is a premium textured vinyl substrate designed for use in banner, awning, marine, and other specialty applications. It is optimized for use with Solvent, UV, and Latex printers. This revolutionary material offers the look, feel, and texture of fabric and offers superior printability, weatherability, and strength.

### Embossed for high-quality, textured fabric look/feel Lightweight; improved flexibility Weather- and stain-resistant Watertight FR Certified

**Added Benefits:** 

Basic Fabric	Standard	Metric
Base Fabric Weight	2.7 oz/yd²	91 g/m²
Fiber / Style	Polyester Low Wick Scrim	

<b>Coated Fabric</b>	Standard	Metric	
Total Weight (Weathertyte PLUS)	16 oz/yd²	542 g/m <sup>2</sup>	
Total Weight (Weathertyte PLUS <i>Lite</i> )	11 oz/yd²	373 g/m²	
Coating Type	PVC		
Sealing Properties	Dielectric	Thermal	

Material Properties	ASTM Test Methods	Weathertyte® PLUS Standard   Metric	Weathertyte® PLUS <i>Lite</i> Standard   Metric
Tensile Strength, Grab (Warp)	D751-A	230 lbs   1,023 N	230 lbs   1,023 N
Tensile Strength, Grab (Fill)	D751-A	150 lbs   667 N	150 lbs   667 N
Tear Strength, Tongue (Warp)	D751-B (mod)	50 lbs   222 N	50 lbs   222 N
Tear Strength, Tongue (Fill)	D751-B (mod)	30 lbs   133 N	30 lbs   133 N
Screwdriver Puncture	D751	50 lbs   222 N	40 lbs   178 N
Ball Puncture	D751	250 lbs   1,112 N	240 lbs   1,068 N
Hydrostatic Resistance	D751-A	300 psi   2.1 MPa	250 psi   1.7 MPa
Abrasion Resistence	D3389	900 cycles	200 cycles
Low Temp Bend	D2136	0°F   -18°C	-10°F   -23°C
High Temp, Cont/Interm.	D1204	180 / 200°F   82 / 93°C	180 / 200°F   82 / 93°C
Mildew/Fungus Resistance	G21	No Growth	
Fire Resistance	E84 NFPA 701 (small scale) NFPA 701 (large scale)	Class A Pass Pass CA State Fire Marshall	

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

# WEATHERTYTE® PLUS




Dark Red \* Shown Above: Weathertyte® PLUS




Black \*\* Shown Above: Weathertyte® PLUS Lite


**Acrylic Topcoat** Weathertyte® PLUS 8-year Warranty Weathertyte® PLUS Lite 5-year Warranty








Green ' Forest Green \*\*



Navy Blue



Charcoal



<sup>\*</sup> Available in Weathertyte® PLUS

<sup>\*\*</sup> Available in Weathertyte® PLUS and Weathertyte® PLUS Lite